

Dry Applications

Maintenance free bearing material for performance demanding dry running applications



GLYCO® 97 design types

For some applications operated without

do not achieve the targeted service

life. Performances in friction improving

the system efficiency are also below

Reasons could be the use of standard performance PTFE-materials, not optimized

and long operation periods.

for dry running conditions at higher loads

any lubrication, maintenance free bearings

Challenge

expectations.


[PTFE+MoS₂+ BN] Steel

Photomicrograph of the 3-layer material (steel back + sliding layer of porous bronze + compound of PTFE and additives)

Solution

GLYCO® 97 is a sliding material especially developed for dry applications. It is distinguished by a high load carrying capacity and wear resistance as well as a low friction coefficient.

Specific additives to the PTFE base material have been used in order to improve these key performance characteristics.



pv-diagram under dry running operation including friction value ranges

Key Features

- Maintenance-free operation lubrication for use under severe dry running conditions
- · High pv-value
- · Good wear resistance
- · High load capacity
- · Low friction
- · Rotating, oscillating and axial motion possible
- Wide range of part design types


Benefit	Details
High Load capacity (dry use)	static: max. 250 MPa
	dynamic: max. 100 MPa
Max. sliding velocity (dry use)	2.0 m/s
p.v. max. value	pv max. = 3.8 MPa x m/s under dry running conditions* *Standard F-M test conditions
Wide operating temperature range	- 200 to 260 °C

Additional Information

GLYCO® 97 is a three layer composite material. A porous tin bronze sinter structure is applied on a steel back. This layer is impregnated with a PTFE sliding material and a specific combination of fillers especially chosen to improve the performance of this material under dry running conditions. On the top of this filled bronze structure, a 5 to 30 µm thick overlay of the same sliding material is applied, providing the initial lubrication during the running-in of the application.

GLYCO® 97 sliding bearings are therefore showing lower friction and in the same time higher wear resistance under dry operation compared to other standard PTFE-based materials. In addition, it is available on request with a thinner top layer offering advantages for applications involving a cataphoretic painting process.

Applications: Automotive dry running systems like vibration dampers, actuators, various hinges (door, trunk lid, hood, convertible roof), locking devices, pedal systems.



Flange design typically used in multiple hinge applications











©2018 Federal-Mogul LLC. All rights reserved. All trademarks are owned by Federal-Mogul LLC or one of its subsidiaries, in one or more countries